Synthesis, Spectroscopic and Thermal Characterization of Non-Metal Cation (NMC) Pentaborates Salts Containing Cations Derived From Histidine and Arginine

Katyonik Histidine ve Arjinin Türevleri İçeren Metal Katyonsuz (NMC) Pentaborat Tuzlarının Sentezi, Spektroskopik ve Termal Karakterizasyonu

Research Article

Dursun Ali Köse^{1,*}, Michael A. Beckett², Naki Çolak¹

¹Hitit University, Faculty of Arts and Sciences, Department of Chemistry, Çorum, Turkey ²Bangor University, School of Chemistry, Bangor, Gwynedd LL57, 2UW, UK

ABSTRACT

The new non-metal cation (NMC) pentaborate structures of cationic histidine and arginine aminoacids were synthesized and characterized using spectroscopic ("B NMR and IR) methods. Their thermal properties have been investigated by TG/DrTG-DTA. The histidine NMC pentaborate, $[C_6H_{10}N_3O_2][B_5O_6(OH)_4].4H_2O$ and the arginine pentaborate, $[C_6H_{13}N_4O_2][B_5O_6(OH)_4]_2.3H_2O$ are formulated with 4 and 3 waters of crystallization, respectively. The histidine pentaborate is more stable than the arginine pentaborate to thermal decomposition, but both decompose thermally via initial dehydration followed by loss of amino acid fragments to afford glassy B_2O_3 .

Key Words

Non-metal cation borate structure, Pentaborate, Thermal investigation, "B NMR

ÖZET

Katyonik histidin ve arjinin aminoasitlerinin metal katyonu içermeyen (NMC) yeni pentaborat yapıları Sentezlendi ve spektroskopik yöntemler ("B NMR and IR) kullanılarak karakterize edildi. Termal özellikleri TG/DrTG-DTA ile araştırıldı. Histidine NMC pentaborat, $[C_6H_{10}N_3O_2][B_5O_6(OH)_4]$.4H₂O ve arjinin pentaborat, $[C_6H_{13}N_4O_2][B_5O_6(OH)_4]$.2H₂O ve arjinin pentaborat, remal olarak histidine pentaborat arjinin pentaborat yapısına göre daha kararlıdır, fakat her iki NMC pentaborat yapısının bozunması dehidrasyonu izleyen aminoasit bölümlerinin uzaklaşması ve bozunma ürünü olarak camsı yapıda B_2O_3 kalmasıyla gerçekleşir.

Anahtar Kelimeler

Metal katyonu içermeyen borat yapısı, Pentaborat, Termal inceleme, ¹¹B NMR

Article History: Received January 19, 2012; Revised March 25, 2012; Accepted May 3, 2012; Available Online: June 19, 2012

 Correspondence to: D.Ali Köse, Hitit University, Faculty of Arts and Sciences, Department of Chemistry, 19000, Çorum, Turkey

 Tel: +90 364 227 70 00 / 1643
 Fax: +90 364 227 70 05

 E-Mail: dalikose@hitit.edu.tr,

dkose@hacettepe.edu.tr

INTRODUCTION

orate materials have attracted a great deal of attention in the past decades because of their rich structural chemistry and potential applications in mineralogy and industry [1-3]. From the structural point of view, boron atoms may coordinate with oxygen atoms not only in three-fold coordination (triangular, BO₂), but also in four-fold coordination (tetrahedral, BO,). The BO₂ and BO₄ groups may be further linked via common oxygen atoms to form polynuclear anions, including isolated rings (or cages), infinite chains, sheets and frameworks [4-10], and salts containing polyanions such as $[B_4O_5(OH)_4]_2$ -[11], $[B_5O_6(OH)_4]_1$ -[12] and $[B_9O_{12}(OH)_6]_3$ -[13] have been reported. Compared to metal borates, the synthesis of borates containing non-metal cations are still a much less explored area, though a few cases have been reported in recent years [3,15-17]. However, no NLO property has been mentioned except for $[C_2H_{10}N_2][B_5O_8(OH)]$ [18] and a few tetrafluoro borates showing NLO properties [19,20]. Therefore, it is significant to explore the NLO properties of nonmetal borates for understanding the NLO effect and searching for new NLO materials.

Non-metal cations differ from metal cations in their potential for interactions with borate anions: metal cations are spherical and primarily accept electron density from oxygen donors, whilst non-metal cations may be non-spherical and may have H-bond donor sites [21]. Steric and electronic factors associated with non-metal cations may be fined-tuned and these properties will affect structure. In this respect, the only borate minerals that do not contain metal counterions (they contain the $[NH_4]_3(B_{15}O_{20}(OH)_8].4H_2O$ and larderellite $[NH_{4}][B_{5}O_{7}(OH)_{2}].H_{2}O$ and these polyborate minerals have anionic structures which are exclusively paired with the ammonium cation. Furthermore, the quanidinium and imidizolium polyborate systems both display the isolated nonaborate anion, $[B_{q}O_{12}(OH)_{6}]_{3}$ -, and this anion is only observed with these non-metal cations [4]. In contrast, pentaborate(1-) salts are particularly stable and have been readily obtained for both metal and non-metal cations [23-25]. Quaternary ammonium and related non-metal pentaborate systems have also been studied but relatively few have been structurally characterized [15,26]. More recently some template complexed metal cation/ pentaborate anion salts have been characterized [25]. In this study, we reported non-metal cation (NMC) pentaborate structures derived from the amino acids histidine and arginine and characterized by spectroscopic and thermal and methods.

EXPERIMENTAL


0.01 mol histidine or arginine amino acids (Sigma-Aldrich) were solved in a mixture of distilled water (40 mL) and methanol (Sigma-Aldrich) (40 mL). Then 0.05 mol H_3BO_3 (Sigma-Aldrich) was added to each solution as solid (scheme 1). The solutions were stirred for 1 hour. The solutions were evaporated until dryness. The white solid products were collected and dried at 50 °C in a vacuum.

The synthesis reactions of histidine and arginine pentaborate were described in below and obtained in a 75% and 65% overall yield respectively. Analytical data are shown in Table 1.

¹¹B NMR spectra (160 MHz, D_2O) of histidine and arginine derived pentaborates were given Figure 1 and 2, respectively. The histidine pentaborate

Molecular Molecular Yield (%) C (%) H (%) N (%) Meltina Formula Weight Point Exp.-Calc. Exp.-Calc. Exp.-Calc. C₆H₂₂B₅N₃O₁₆ 446.32 g/mol 86% 98 °C 16.24-16.11 4.98-4.70 9.41-9.40 666.44 g/mol 75% 73°C 10.70-10.77 4.87-4.35 C₆H₃₀B₁₀N₄O₂₅ 8.31-8.38

Table 1. Analytical results of histidine and arginine derived pentaborates:



Scheme 1. Showig of reaction of histidine (1) and arginine (2) with boric acid.

spectrum has three peaks that are at 19.17 ppm attributed to trigonal free boric acid, at 13.33 ppm attributed to triborate structure and at 1.09 ppm tetrahedral centre of pentaborate structure. The peaks of arginine pentaborate are similar to the histidine pentaborate spectrum with peaks at 18.70 ppm, 13.04 ppm and 1.05 ppm. These peaks belong to free boric acid, triborate structure and pentaborate structure, respectively. These results agree with previous literature [26-28]. The "B NMR spectra of the histidine and arginine pentaborate salts are complex but explainable in terms of a complex series of equilibra existing in aqueous solution which link monomeric and oligomeric borate species [27].

The surface area of histidine pentaborate is 3.5 m² and the arginine pentaborate is 0.9 m² according to single point BET analysis.




Figure 1."B NMR curve of histidine pentaborate structure.

The TGA/DTA curves of histidine and arginine pentaborate salts are shown Figure 3. TG data were recorded in the temperature range of 25-1000 °C in nitrogen media for both of them. The decomposition of histidine pentaborate has three stage processes. Firstly, four molecules hydrated waters remove in 95-195 °C range (exp. 14.18%; calc. 16.14%). The dehydration of compound occurs at 98 °C and 128 °C in two endothermic steps. The second stage belongs to removing of two water molecules from the pentaborate structure in 202-240 °C range with endothermic DTA peak at 215 °C (exp. 7.25%; calc. 8.07%). The organic cation histidine is decomposed at last stage process in 251-448 °C range with endothermic DTA peaks at 293 °C and 322 °C. Finally, a glassy B₂O₃ oxide was obtained as decomposition product of histidine pentaborate salt (exp. 41.53%; calc. 39.23%). The decomposition peaks of arginine pentaborate are




Figure 2.¹¹B NMR curve of arginine pentaborate structure.

Sample	Temperature Range (°C)	DTGmax (°C)	Removed Group	Mass loss (%) Exp Calc.	Total mass (%) Exp Calc.	Decomposition Product
C ₆ H ₂₂ B ₅ N ₃ O ₁₆	95-195	98,128	4 H ₂ 0	14.18-16.14		C ₆ H ₁₄ B ₅ N ₃ O ₁₂
	202-240	215	2 H ₂ 0	7.25-8.07		$C_6 H_{10} B_5 N_3 O_{10}$
	251-448	293, 322	$C_{6}H_{14}N_{3}O_{2}$	33.15-33.79	41.53-39.23	5/2 B ₂ O ₃
$C_6H_{30}B_{10}N_4O_{25}$	90-140	132	3 H ₂ 0	9.08-8.14		$C_6 H_{24} B_{10} N_4 O_{22}$
	200-226	208	4 H ₂ 0	11.04-10.80		$C_6H_{16}B_{10}N_4O_{18}$
	238-511	346	C ₆ H ₁₆ N ₄ O ₂	27.52-26.15	54.53-52.56	5 B ₂ O ₃

Table 2. Decomposition data (TGA/DTA) of histidine and arginine pentaborate structure.

similar to histidine pentaborate. According to TGA curves, it has three decomposition stage. Their first, removing of three molecules hydrated waters that occurs in 90-140 °C range with the endothermic DTA peak at 132 °C (exp. 9.08%; calc. 8.14%). The second stage consists removing of four molecules water from two pentaborate structure in 200-226 °C range with the endothermic DTA peak at 208 °C (exp. 11.04%; calc. 10.80%). At the third stage, the organic cation arginine removes from the structure in 238-511 °C range with endothermic DTA peak at 346 °C (exp. 27.52%; calc. 26.15%). Lastly, a glassy B_2O_3 residue remains in the analysis capsule as decomposition product (exp. 54.53%; calc. 52.56%).

The FT-IR spectrum curves of histidine and arginine derived pentaborates are presented in Figure 4. The very strong bands at 1419 and 1310 cm⁻¹ for histidine pentaborate and 1427 and 1303 cm⁻¹ for arginine pentaborate are symmetric and symmetric vibrations of B-O in BO₃, whereas the bands at 1030, 919 and 901 cm⁻¹ for histidine pentaborate and 1022, 923 and 905 cm⁻¹ for arginine pentaborate are typical of asymmetric and symmetric stretching modes of B-O in BO_4 , respectively [29-32]. The peaks at 1188 cm⁻¹ for histidine pentaborate and 1149 cm⁻¹ for arginine pentaborate are the inplane bending mode of B-O-H while, the out-ofplane bending modes of B-O in BO₃ are obtained at 703 cm⁻¹ for histidine and 707 cm⁻¹ for arginine pentaborate structures. The weak peak at 1684 cm⁻¹ and 1663 cm⁻¹ belong to bending of NH₂ groups [33]. Moreover, the bands at 3147 cm⁻¹ and 3230 cm⁻¹ are correspond to the N-H stretching vibrations of histidine and arginine pentaborates respectively. Finally, the O-H stretching bands are appeared

at 3412 cm^{-1} for histidine derived pentaborate and 3455 cm^{-1} for arginine pentaborate.

CONCLUSION

The NMC pentaboerate salts derived from histidine, $[C_6H_{10}N_3O_2][B_5O_6(OH)_4].4H_2O$, and arginine, $[C_6H_{13}N_4O_2][B_5O_6(OH)_4]_2.3H_2O$, have been synthesized and characterized by elemental analysis, spectroscopy (¹¹B NMR and IR) and thermal (TG/DrTG-DTA) methods and formulated with 4 and 3 waters of crystallization, respectively. TGA/DTA analysis showed dehydration, followed by decomposition of the amino acid fragments to leave glassy B_2O_3 residue were obtained.Thermal stability of the samples ranged as follows: histidine pentaborate > arginine pentaborate.

REFERENCES

- C.L. Christ, J.R. Clark, A crystal-chemical classification of borate structures with emphasis on hydrated borates, Phys. Chem. Miner. 2 (1977) 59.
- P.C. Burns, Borate clusters and fundamental building blocks containing four polyhedra; why few clusters are utilized as fundamental building blocks of structures, Can. Mineral. 33 (1995) 1167.
- (a) G.M. Wang, Y.Q. Sun, G.Y. Yang, Syntheses and crystal structures of two new pentaborates, J. Solid State Chem. 178 (2005) 729; (b) G.M. Wang, Y.Q. Sun, G.Y. Yang, Synthesis and characterization of a new layered lead borate, J. Solid State Chem. 179 (2006) 398.




Figure 3. TGA/DTA curves of histidine (I) and arginine (II) pentaborate structure.




Figure 4. FT-IR graphic of histidine (I) and arginine (II) pentaborate structure.

- D.M. Schubert, M.Z. Visi, C.B. Knobler, Guanidinium and Imidazolium Borates Containing the First Examples of an Isolated Nonaborate Oxoanion: [B9012(OH)6]3-, Inorg. Chem. 39 (2000) 2250.
- M. Touboul, N. Penin, G. Nowogrocki, Crystal Structure and Thermal Behavior of Cs₂[B₄O₅(OH)₄]₃H₂O, J. Solid State Chem. 143 (1999) 260.
- D.M. Schubert, F. Alam, M.Z. Visi, C.B. Knobler, Structural Characterization and Chemistry of the Industrially Important Zinc Borate, Zn[B₃O₄(OH)₃], Chem. Mater. 15 (2003) 866.
- 7. Z.T. Yu, Z. Shi, Y.S. Jiang, H.M. Yuan, J.S. Chen, A chiral lead borate containing infinite and finite chains built up from BO_4 and BO_3 units, Chem. Mater. 14 (2002) 1314.
- 8. N. Penin, M. Touboul, G. Nowogrocki, Crystal Structure of a New Form of Sodium Octoborate β -Na₂B₈O₁₃, J. Solid State Chem. 168 (2002) 316.
- 9. H. Huppertz , B. von der Eltz , Multianvil High-Pressure Synthesis of $Dy_4B_6O_{15}$: The First Oxoborate with Edge-Sharing BO_4 Tetrahedra, J. Am. Chem. Soc. 2002 , 124 , 9376.
- M. Touboul, N. Penin, G. Nowogrocki, Borates: a survey of main trends concerning crystal-chemistry, polymorphism and dehydration process of alkaline and pseudo-alkaline borates, Solid State Sci. 5 (2003) 1327.
- (a) C.J. Carmalt, W. Clegg, A.H. Cowley, F.J. Lawlor, T.B. Marder, N.C. Norman, C.R. Rice, O.J. Sandoval, A.J. Scott, Isolation and structural characterization of novel compounds containing B₄O₂ rings, Polyhedron 16 (1997) 2325; (b) T.J.R. Weakley, Guanidinium tetraborate(2-) dihydrate, (CH₆N₃)₂[B₄O₅(OH)₄].2H₂O, Acta Crystallogr. Sect. Cryst. Struct. Commun. 41 (1985) 377; (c) A.S. Batsanov, E.H. Nava, T. Struchkov, V.M. Akimov, Ethylenediammonium tetraborate dihydrate, C₂H₁₄B₄N₂O₉, Cryst. Struct. Commun. 11 (1982) 1629.
- 12. (a)C.C.Freyhardt, M.Wiebcke, J.Felsche, G.Engelhardt, $N(nPr)_{4}[B_{5}O_{6}(OH)_{4}][B(OH)_{3}]_{2}$ and $N(nBu)_{4}[B_{5}O_{6}(OH)_{4}]$ [B(OH)₃]₂: clathrates with a diamondoid arrangement of hydrogen-bonded pentaborate anions, J. Inclusion Phenom. Macrocyclic Chem. 18 (1994) 161; (b) Li, Qi; Mak, C. W. Thomas, Novel inclusion compounds of urea with tetraalkylammonium pentaborates, Supramol. Chem. 8 (1997) 147; (c) A.N. Chekhlov, I.V. Martynov, Crystal structure of 1,10-diazonia-18-crown-6 bis(tetrahydroxypentaborate) hexahydrate, Proc. Natl. Acad. Sci. USSR 362 (1998) 648; (d) K.M. Turdybekov, Yu.T. Struchkov, V.M. Akimov, V.G. Skvortsov, O.V. Petrova, Sh.V. Sadetinov, Crystal structure of tributylammonium tetrahydroxohexaoxopentaborate. bis(boron hydroxide), Zh. Neorg. Khim. 37 (1992) 1250.

- P.C. Burns, J.D. Grice, F.C. Hawthorne, Borate minerals. I. Polyhedral clusters and fundamental building blocks, Can. Mineral. 33 (1995) 1131.
- J.D. Grice, P.C. Burns, F.C. Hawthorne, Borate minerals. II. Ahierarchy of structures based upon the borate fundamental building blocks, Can. Mineral. 37 (1999) 731.
- 15. M.Z. Visi, C.B. Knobler, J.J. Owen, M.I. Khan, D.M. Schubert, Cryst. Growth Des. 6 (2006) 538.
- Z.H. Liu, L.Q. Li, W.J. Zhang, Two New Borates Containing the First Examples of Large Isolated Polyborate Anions: Chain [B7O9(OH)5]2– and Ring [B14020(OH)6]4–, Inorg. Chem. 45 (2006) 1430.
- C.Y. Pan, G.M. Wang, S.T. Zheng, G.Y. Yang, [NH₃CH₂CHCH₃NH₃][B₈O₁₁(OH)₄].H₂O: Synthesis and characterization of the first 1D borate template by 1,2-diaminopropane, J. Solid State Chem. 180 (2007) 1553.
- 18. S.H. Yang, G.B. Li, S.T. Tian, J.H. Lin, Synthesis and Structure of $[C_2H_{10}N_2][B_5O_8(OH)]$: A Nonmetal Pentaborate with Nonlinear Optical Properties, Cryst. Growth Des. 7 (2007) 1246.
- V. Guieu, C. Payrastre, Y. Madaule, S. Garcia-Alonso, P.G. Lacroix, K. Nakatani, Large Quadratic Nonlinear Optical Efficiencies in Pseudosymmetric Streptocyanine Dyes, Chem. Mater. 18 (2006) 3674.
- J. Ramajothi, S. Dhanuskodi, Optical and microhardness studies of semiorganic nonlinear optical material: L- histidine tetrafluoroborate, Cryst. Res. Technol. 38 (2003) 986.
- D.M. Schubert, R.A. Smith, and M.Z. Visi, Studies of crystalline nonmetal borates, Glass Technol. 44 (2003) 63.
- (a) S. Merlino and F. Sartori, Ammonioborite: new borate polyion and its structure, Science 171 (1971) 377; (b) S. Merlino and F. Sartori, The crystal structure of larderellite, NH₄B₅O₇(OH)₂.H₂O, Acta Cryst. B. 25 (1969) 2264.
- 23. (a) M. Wiebcke, C.C. Freyhardt, J. Felsche, and G. Englehardt, Clathrates with three-dimensional host structures of hydrogen-bonded pentaborate [B₅O₆(OH)₄]-ions: pentaborates with the cations NMe⁴⁺, NEt⁴⁺, NPhMe³⁺ and pipH⁺ (pipH⁺=piperidinium), Z. Naturfoirch B 48 (1993) 978; (b) H.X. Zhang, S.T. Zheng and G.Y. Yang, Tetramethylammonium pentaborate 0.25-hydrate, Acta Cryst. C 60 (2004) o545; (c) R.A. Barber, J.P.H. Charmant, N.C. Norman, A.G. Orpen, and J. Rossi, Dimethylammonium tetrahydropentaborate, Acta Cryst E 60 (2004) o1086; (d) B.D. Vineyard and H.C. Godt, Jr., A Study of the Reaction of Boric Acid with Amines: Hydroxyboroxin-Amine Salts, Inorg. Chem. 3 (1964) 1144.

- 24. G. Heller, A survey of structural types of borates and polyborates. in F.L. Boschke (ed.), Topics in Current Chemistry 131 (1986) 39.
- 25. (a) G.M.Wang, Y.Q. Sun, and G.Y. Yang, Syntheses and crystal structures of three new borates templated by transition-metal complexes in situ, J. Solid State Chemistry 179 (2006) 1545; H.X. Zhang, S.T. Zheng and G.Y. Yang, Pentaethylenehexamine manganese(II) pentaborate, Acta Cryst. C 60 (2004) m241.
- M.A. Beckett, C.C. Bland, S.J. Coles, P.N. Horton and M.B. Hursthouse, Supramolecular structures containing 'isolated' pentaborate anions and nonmetal cations: Crystal structures of [Me₃NCH₂CH₂OH] [B₅O₆(OH)₄] and [4-MepyH, 4-Mepy][B₅O₆(OH)₄], J. Organomet. Chem. 692 (2007) 2832.
- C.G. Salentine, High-field boron-11 NMR of alkali borates. Aqueous polyborate equilibria, Inorg. Chem. 22 (1983) 3920.

- M.A. Beckett, P.N. Horton, M.B. Hursthouse, D.A. Knox, J.L. Timmis, Structural (XRD) and thermal (DSC, TGA) and BET analysis of materials derived from non-metal cation pentaborate salts, Dalton Trans. 39 (2010) 3944.
- 29. C.E. Weir, Infrared spectra of the hydrated borates, J. Res. Naufl. Bur. Stand. Sect. A 70 (1966) 153.
- C.E. Weir, R. Schroeder, Infrared Spectra of Crystalline Inorganic Borates, J. Res. Naufl. Bur. Stand. Sect. A 68 (1964) 465.
- J. Krough-Moe, Interpretation of the Infra-red Spectra of Boron. Oxide and Alkali Borate Glasses, Phys. Chem. Glases, 6 (1965) 46.
- Y. Yang, Y. Wang, J. Sun, M. Cui, C. Meng, Synthesis, Crystal Structure, and Characterization of a Novel MetalloOrganically–Templated Pentaborate with Mixed Ligands, Z. Anorg. Allg. Chem. 637 (2011) 729.
- 33. Z.H. Liu, J.J. Zhang, W.J. Zhang, Synthesis, crystal structure and vibrational spectroscopy of a novel mixed ligands Ni(II) pentaborate: $[Ni(C_4H_{10}N_2)(C_2H_8N_2)_2][B_5O_6(OH)_4]_2$, Inorg, Chim. Acta 359 (2006) 519.